



*Fire Pits accents are meant to demonstrate stone appearance and may not necessarily be taken from Polycor Hardscapes & Masonry projects.



*Computer generated images and printed reproductions may not accurately match natural stone colors.

EASTERN GRAY™ GRANITE

Sourced from three different North American quarries, this granite is light to medium gray in color with a mid-size coarse grain. It is highly prized for its consistency in color.

Physical Test Results

		IMPERIAL	METRIC
Absorption by weight	ASTM C97	0.252%	0.252%
Density	ASTM C97	165 lb/ft ³	2 634.05 kg/m ³
Compressive Strength	ASTM C170	17 007 Psi	117.26 MPa
Modulus of rupture	ASTM C99	1 617 Psi	11.15 MPa
Flexural strength	ASTM C880	1 374 Psi	9.50 MPa

